



Version 10 x d - Uncoated

Materials group	Material	Material number	DIN	AISI/ASTM/UNS	v _c up to [SFM]	Q ₁	Q _x	Ød ₁	Ød ₁	Ød ₁	Ød ₁	Ød ₁	Ød ₁	Ød ₁	Ød ₁	Ød ₁	Ød ₁
								.0315 f [IPR]	.0394 f [IPR]	.0492 f [IPR]	.0591 f [IPR]	.0787 f [IPR]	.0984 f [IPR]	.1181 f [IPR]	.1575 f [IPR]	.1969 f [IPR]	.2362 f [IPR]
P	Unalloyed carbon steel R _m < 800 N/mm ²	1.0301	C10	AISI 1010	197	6xd ₁	2xd ₁	.0022	.0031	.0043	.0055	.0071	.0083	.0094	.0110	.0122	.0134
		1.0401	C15	AISI 1015													
		1.1191	C45E/CK45	AISI 1045													
		1.0044	S275JR	AISI 1020													
		1.0715	11SMn30	AISI 1215													
	Low alloyed steel R _m > 900 N/mm ²	1.5752	15NiCr13	ASTM 3415 / AISI 3310	197	6xd ₁	2xd ₁	.0022	.0031	.0039	.0047	.0059	.0067	.0075	.0087	.0094	.0102
		1.7131	16MnCr5	AISI 5115													
		1.3505	100Cr6	AISI 52100													
		1.7225	42CrMo4	AISI 4140													
		1.2842	90MnCrV8	AISI O2													
High alloyed tool steel R _m < 1200 N/mm ²	1.2379	X153CrMoV12	AISI D2	131	6xd ₁	2xd ₁	.0008	.0020	.0026	.0031	.0043	.0051	.0059	.0071	.0079	.0087	
	1.2436	X210CrW12	AISI D4/D6														
	1.3343	H56-5-2C	AISI M2 / UNS T11302														
	1.3355	H518-0-1	AISI T1 / UNS T12001														
M	Stainless steel ferritic	1.4016	X6Cr17	AISI 430 / UNS S43000													
		1.4105	X6CrMoS17	AISI 430F													
	Stainless steel martensitic	1.4034	X46Cr13	AISI 420C													
		1.4112	X90CrMoV18	AISI 440B													
	Stainless steel martensitic - PH	1.4542	X5CrNiCuNb 16-4	AISI 630 / ASTM 17-4 PH													
		1.4545	X5CrNiCuNb 15-5	ASTM 15-5 PH													
	Stainless steel austenitic	1.4301	X5CrNi 18-10	AISI 304													
		1.4435	X2CrNiMo 18-14-3	AISI 316L													
1.4441		X2CrNiMo 18-14-3	AISI 316LM														
1.4539		X1NiCrMoCu 25-20-5	AISI 904L														
K	Cast iron	0.6020	GG20	ASTM 30													
		0.6030	GG30	ASTM 40B													
		0.7040	GGG40	ASTM 60-40-18													
		0.7060	GGG60	ASTM 80-60-03													

←----- Recommended: CrazyDrill Cool 10 x d, coated ----->

←----- Recommended: CrazyDrill Cool 10 x d, coated ----->



Your contacts

Mikron Tool SA Agno
P.O. Box 340
6934 Bioggio
Switzerland
Phone +41 91 610 40 00
Fax +41 91 610 40 10
mto@mikron.com

Mikron GmbH Rottweil
Abteilung Werkzeuge
Bernener Feld 71
78628 Rottweil
Germany
Phone +49 741 5380 450
Fax +49 741 5380 480
info.mtr@mikron.com

Mikron Corp. Monroe
P.O. Box 268
200 Main Street
Monroe, CT 06468
USA
Phone +1 203 261 3100
Fax +1 203 268 4752
mmo@mikron.com



Version 10 x d - Uncoated

Materials group	Material	Material number	DIN	AISI/ASTM/UNS	v _c up to [SFM]	Q ₁	Q _x	Ød ₁	Ød ₁	Ød ₁	Ød ₁	Ød ₁	Ød ₁	Ød ₁	Ød ₁	Ød ₁	Ød ₁
								.0315 f [IPR]	.0394 f [IPR]	.0492 f [IPR]	.0591 f [IPR]	.0787 f [IPR]	.0984 f [IPR]	.1181 f [IPR]	.1575 f [IPR]	.1969 f [IPR]	.2362 f [IPR]
N	Aluminium alloy wrought	3.2315	AlMgSi1	ASTM 6351	984	10xd ₁	-	.0016	.0020	.0024	.0030	.0031	.0039	.0047	.0055	.0067	.0079
		3.4365	AlZnMgCu1.5	ASTM 7075													
	Aluminium alloy cast	3.2163	GD-ALSi9Cu3	ASTM A380	656	10xd ₁	-	.0024	.0028	.0031	.0039	.0047	.0059	.0067	.0079	.0087	.0098
		3.2381	GD-ALSi10Mg	UNS A03590													
	Copper	2.004	Cu-OF / CW008A	UNS C10100	328	3/2xd ₁	1xd ₁	.0018	.0022	.0028	.0031	.0035	.0039	.0043	.0051	.0059	.0075
		2.0065	Cu-ETP / CW004A	UNS C11000													
	Brass lead free	2.0321	CuZn37 CW508L	UNS C27400	459	1xd ₁	1/2xd ₁	.0018	.0022	.0028	.0031	.0035	.0039	.0043	.0051	.0059	.0075
		2.036	CuZn40 CW509L	UNS C28000													
	Brass, Bronze R _m < 400 N/mm ²	2.0401	CuZn39Pb3 / CW614N	UNS C38500	394	2xd ₁	1xd ₁	.0028	.0035	.0039	.0047	.0053	.0059	.0067	.0075	.0079	.0087
		2.102	CuSn6	UNS C51900													
Bronze R _m < 600 N/mm ²	2.0966	CuAl10Ni5Fe4	UNS C63000	394	10xd ₁	-	.0006	.0010	.0014	.0020	.0026	.0033	.0039	.0047	.0055	.0075	
	2.096	CuAl9Mn2	UNS C63200														
S ₁	Super alloys	2.4856		Inconel 625													
		2.4668		Inconel 718													
		2.4617	NiMo28	Hastelloy B-2													
		2.4665	NiCr22Fe18Mo	Hastelloy X													
S ₂	Titanium pure	3.7035	Gr.2	ASTM B348 / F67	66	1/2xd ₁	1/4xd ₁	.0004	.0008	.0014	.0020	.0026	.0031	.0035	.0039	.0047	.0055
		3.7065	Gr.4	ASTM B348 / F68													
	Titanium alloys	3.7165	TiAl6V4	ASTM B348 / F136	66	1/2xd ₁	1/4xd ₁	.0004	.0008	.0014	.0020	.0026	.0031	.0035	.0039	.0047	.0055
9.9367		TiAl6Nb7	ASTM F1295														
S ₃	Cr-Co alloys	2.4964	CoCr20W15Ni	Haynes 25													
			CrCoMo28	ASTM F1537													
H ₁	Hardened steel < 55 HRC	1.2510	100MnCrMoW4	AISI O1													
H ₂	Hardened steel ≥ 55 HRC	1.2379	X153CrMoV12	AISI D2													

← ----- Recommended: CrazyDrill Cool 10 x d, coated ----- →

← ----- Recommended: CrazyDrill Cool 10 x d, coated ----- →

← ----- Recommended: CrazyDrill Cool 10 x d, coated ----- →



Your contacts

Mikron Tool SA Agno
P.O. Box 340
6934 Bioggio
Switzerland
Phone +41 91 610 40 00
Fax +41 91 610 40 10
mto@mikron.com

Mikron GmbH Rottweil
Abteilung Werkzeuge
Berner Feld 71
78628 Rottweil
Germany
Phone +49 741 5380 450
Fax +49 741 5380 480
info.mtr@mikron.com

Mikron Corp. Monroe
P.O. Box 268
200 Main Street
Monroe, CT 06468
USA
Phone +1 203 261 3100
Fax +1 203 268 4752
mmo@mikron.com