

Materials group	Material	Material number	DIN	AISI/ASTM/UNS	v <sub>c</sub> up to [m/min]	Q <sub>1</sub>	Q <sub>x</sub>	Ød <sub>1</sub>	Ød <sub>1</sub>	Ød <sub>1</sub>	Ød <sub>1</sub>	Ød <sub>1</sub>	Ød <sub>1</sub>	Ød <sub>1</sub>	Ød <sub>1</sub>	Ød <sub>1</sub>	Ød <sub>1</sub>	Ød <sub>1</sub>
								0.40 f [mm/rev]	0.80 f [mm/rev]	1.00 f [mm/rev]	1.25 f [mm/rev]	1.50 f [mm/rev]	2.00 f [mm/rev]	2.50 f [mm/rev]	3.00 f [mm/rev]	4.00 f [mm/rev]	5.00 f [mm/rev]	6.00 f [mm/rev]
P	Unalloyed carbon steel R <sub>m</sub> < 800 N/mm <sup>2</sup>	1.0301	C10	AISI 1010	120	4xd <sub>1</sub>	-	0.040	0.100	0.120	0.150	0.200	0.250	0.270	0.350	0.370	0.390	0.400
		1.0401	C15	AISI 1015														
		1.1191	C45E/CK45	AISI 1045														
		1.0044	S275JR	AISI 1020														
		1.0715	11SMn30	AISI 1215														
	Low alloyed steel R <sub>m</sub> > 900 N/mm <sup>2</sup>	1.5752	15NiCr13	ASTM 3415 / AISI 3310	80	4xd <sub>1</sub>	-	0.015	0.030	0.080	0.120	0.160	0.200	0.230	0.250	0.270	0.300	0.320
		1.7131	16MnCr5	AISI 5115														
		1.3505	100Cr6	AISI 52100														
		1.7225	42CrMo4	AISI 4140														
		1.2842	90MnCrV8	AISI O2														
	High alloyed tool steel R <sub>m</sub> < 1200 N/mm <sup>2</sup>	1.2379	X153CrMoV12	AISI D2	60	4xd <sub>1</sub>	-	0.020	0.070	0.120	0.150	0.200	0.250	0.280	0.300	0.320	0.340	0.350
		1.2436	X210CrW12	AISI D4/D6														
1.3343		HS6-5-2C	AISI M2 / UNS T11302															
1.3355		HS18-0-1	AISI T1 / UNS T12001															
M	Stainless steel ferritic	1.4016	X6Cr17	AISI 430 / UNS S43000														
		1.4105	X6CrMoS17	AISI 430F														
	Stainless steel martensitic	1.4034	X46Cr13	AISI 420C														
		1.4112	X90CrMoV18	AISI 440B														
	Stainless steel martensitic - PH	1.4542	X5CrNiCuNb 16-4	AISI 630 / ASTM 17-4 PH														
		1.4545	X5CrNiCuNb 15-5	ASTM 15-5 PH														
	Stainless steel austenitic	1.4301	X5CrNi 18-10	AISI 304														
1.4435		X2CrNiMo 18-14-3	AISI 316L															
1.4441		X2CrNiMo 18-14-3	AISI 316LM															
1.4539	X1NiCrMoCu 25-20-5	AISI 904L																
K	Cast iron	0.6020	GG20	ASTM 30	150	4xd <sub>1</sub>	-	0.040	0.150	0.200	0.250	0.300	0.350	0.400	0.450	0.470	0.490	0.500
		0.6030	GG30	ASTM 40B														
		0.7040	GGG40	ASTM 60-40-18														
		0.7060	GGG60	ASTM 80-60-03														
N	Aluminium alloy wrought	3.2315	AlMgSi1	ASTM 6351	220	4xd <sub>1</sub>	-	0.045	0.060	0.080	0.095	0.110	0.130	0.150	0.180	0.190	0.210	0.250
		3.4365	AlZnMgCu1.5	ASTM 7075														
	Aluminium alloy cast	3.2163	GD-AlSi9Cu3	ASTM A380	200	4xd <sub>1</sub>	-	0.040	0.055	0.075	0.085	0.100	0.120	0.140	0.170	0.180	0.200	0.240
		3.2381	GD-AlSi10Mg	UNS A03590														
	Copper	2.004	Cu-OF / CW008A	UNS C10100	120	3/2xd <sub>1</sub>	1xd <sub>1</sub>	0.030	0.050	0.060	0.065	0.075	0.080	0.095	0.110	0.130	0.160	0.200
		2.0065	Cu-ETP / CW004A	UNS C11000														
	Brass lead free	2.0321	CuZn37 CW508L	UNS C27400	150	3/2xd <sub>1</sub>	1xd <sub>1</sub>	0.030	0.050	0.065	0.700	0.075	0.090	0.110	0.140	0.160	0.200	0.220
		2.036	CuZn40 CW509L	UNS C28000														
	Brass, Bronze R <sub>m</sub> < 400 N/mm <sup>2</sup>	2.0401	CuZn39Pb3 / CW614N	UNS C38500	100	3/2xd <sub>1</sub>	1xd <sub>1</sub>	0.035	0.055	0.070	0.800	0.090	0.110	0.130	0.150	0.180	0.220	0.240
		2.102	CuSn6	UNS C51900														
Bronze R <sub>m</sub> < 600 N/mm <sup>2</sup>	2.0966	CuAl10Ni5Fe4	UNS C63000	100	4xd <sub>1</sub>	-	0.015	0.025	0.035	0.050	0.060	0.075	0.095	0.110	0.130	0.160	0.220	
	2.096	CuAl9Mn2	UNS C63200															
S <sub>1</sub>	Super alloys	2.4856		Inconel 625	40	1xd <sub>1</sub>	1/4xd <sub>1</sub>	0.002	0.004	0.005	0.006	0.007	0.010	0.012	0.015	0.020	0.025	0.030
		2.4668		Inconel 718														
		2.4617	NiMo28	Hastelloy B-2														
		2.4665	NiCr22Fe18Mo	Hastelloy X														
S <sub>2</sub>	Titanium pure	3.7035	Gr.2	ASTM B348 / F67	40	1xd <sub>1</sub>	1/4d <sub>1</sub>	0.012	0.024	0.030	0.400	0.045	0.060	0.075	0.090	0.120	0.150	0.180
		3.7065	Gr.4	ASTM B348 / F68														
	Titanium alloys	3.7165	TiAl6V4	ASTM B348 / F136	20	1xd <sub>1</sub>	1/3d <sub>1</sub>	0.020	0.030	0.040	0.500	0.055	0.070	0.080	0.100	0.140	0.160	0.200
9.9367		TiAl6Nb7	ASTM F1295															
S <sub>3</sub>	Cr-Co alloys	2.4964	CoCr20W15Ni CrCoMo28	Haynes 25 ASTM F1537	30	4xd <sub>1</sub>	-	0.006	0.012	0.015	0.020	0.025	0.030	0.035	0.045	0.060	0.075	0.090
H <sub>1</sub>	Hardened steel < 55 HRC	1.2510	100MnCrMoW4	AISI O1	30	4xd <sub>1</sub>	-	0.005	0.007	0.010	0.011	0.012	0.015	0.020	0.025	0.030	0.035	0.040
H <sub>2</sub>	Hardened steel ≥ 55 HRC	1.2379	X153CrMoV12	AISI D2														

Your contacts

**Mikron Tool SA Agno**  
P.O. Box 340  
6934 Bioggio  
Switzerland  
Phone +41 91 610 40 00  
Fax +41 91 610 40 10  
mto@mikron.com

**Mikron GmbH Rottweil**  
Abteilung Werkzeuge  
Berner Feld 71  
78628 Rottweil  
Germany  
Phone +49 741 5380 450  
Fax +49 741 5380 480  
info.mtr@mikron.com

**Mikron Corp. Monroe**  
P.O. Box 268  
200 Main Street  
Monroe, CT 06468  
USA  
Phone +1 203 261 3100  
Fax +1 203 268 4752  
mmo@mikron.com

