




# CrazyDrill Cool 10 x d - uncoated

RECOMMENDATION FOR USE  
● Excellent | ● Good | ○ Acceptable | ☒ Not recommended



## DRILLING WITH INTERNAL COOLING | CUTTING DATA OVERVIEW



Materials group	Material	Mat. no.	DIN	AISI/ASTM/UNS	v <sub>c</sub> [m/min]	Q <sub>1</sub>	Q <sub>x</sub>	f [mm/rev]													
								Ød1													
								0.8 mm	1.0 mm	1.25 mm	1.5 mm	2.0 mm	2.5 mm	3.0 mm	4.0 mm	5.0 mm	6.0 mm				
	f	f	f	f	f	f	f	f	f	f	f	f	f	f	f	f	f	f	f		
P	Unalloyed carbon steel Rm < 800 N/mm²	1.0301	C10	AISI 1010	60	6xd1	2xd1														
		1.0401	C15	AISI 1015																	
		1.1191	C45E/CK45	AISI 1045																	
		1.0044	S275JR	AISI 1020																	
		1.0715	11SMn30	AISI 1215																	
	Low alloyed steel Rm > 900 N/mm²	1.5752	15NiCr13	ASTM 3415 / AISI 3310	60	6xd1	2xd1														
		1.7131	16MnCr5	AISI 5115																	
		1.3505	100Cr6	AISI 52100																	
		1.7225	42CrMo4	AISI 4140																	
		1.2842	90MnCrV8	AISI O2																	
	High alloyed tool steel Rm < 1200 N/mm²	1.2379	X153CrMoV12	AISI D2	40	6xd1	2xd1														
		1.2436	X210CrW12	AISI D4/D6																	
1.3343		HS6-5-2C	AISI M2 / UNS T11302																		
1.3355		HS18-0-1	AISI T1 / UNS T12001																		
M	Stainless steel ferritic	1.4016	X6Cr17	AISI 430 / UNS S43000																	
		1.4105	X6CrMoS17	AISI 430F																	
	Stainless steel martensitic	1.4034	X46Cr13	AISI 420C																	
		1.4112	X90CrMoV18	AISI 440B																	
	Stainless steel martensitic – PH	1.4542	X5CrNiCuNb 16-4	AISI 630 / ASTM 17-4 PH																	
		1.4545	X5CrNiCuNb 15-5	ASTM 15-5 PH																	
	Stainless steel austenitic	1.4301	X5CrNi 18-10	AISI 304																	
		1.4435	X2CrNiMo 18-14-3	AISI 316L																	
1.4441		X2CrNiMo 18-15-3	AISI 316LM																		
	1.4539	X1NiCrMoCu 25-20-5	AISI 904L																		
K	Cast iron	0.6020	GG20	ASTM 30																	
		0.6030	GG30	ASTM 40B																	
		0.7040	GGG40	ASTM 60-40-18																	
		0.7060	GGG60	ASTM 80-60-03																	
N	Aluminium alloy wrought	3.2315	AlMgSi1	ASTM 6351	300	10xd1	-														
		3.4365	AlZnMgCu1.5	ASTM 7075																	
	Aluminium alloy cast	3.2163	GD-AlSi9Cu3	ASTM A380	200	10xd1	-														
		3.2381	GD-AlSi10Mg	UNS A03590																	
	Copper	2.004	Cu-OF / CW008A	UNS C10100	100	1.5xd1	1xd1														
		2.0065	Cu-ETP / CW004A	UNS C11000																	
	Brass lead free	2.0321	CuZn37 CW508L	UNS C27400	140	1xd1	0.5xd1														
		2.036	CuZn40 CW509L	UNS C28000																	
Brass, Bronze Rm < 400 N/mm²	2.0401	CuZn39Pb3 / CW614N	UNS C38500	120	2xd1	1xd1															
	2.102	CuSn6	UNS C51900																		
Bronze Rm < 600 N/mm²	2.0966	CuAl10Ni5Fe4	UNS C63000	120	10xd1	-															
	2.096	CuAl9Mn2	UNS C63200																		
S <sub>1</sub>	Super alloys	2.4856		Inconel 625																	
		2.4668		Inconel 718																	
		2.4617	NiMo28	Hastelloy B-2																	
		2.4665	NiCr22Fe18Mo	Hastelloy X																	
S <sub>2</sub>	Titanium pure	3.7035	Gr.2	ASTM B348 / F67	20	0.5xd1	0.25xd1														
		3.7065	Gr.4	ASTM B348 / F68																	
S <sub>2</sub>	Titanium alloys	3.7165	TiAl6V4	ASTM B348 / F136	20	0.5xd1	0.25xd1														
		9.9367	TiAl6Nb7	ASTM F1295																	
S <sub>3</sub>	CrCo alloys	2.4964	CoCr20W15Ni	Haynes 25																	
			CrCoMo28	ASTM F1537																	
H <sub>1</sub>	Hardened steel < 55 HRC	1.2510	100MnCrMoW4	AISI O1																	
H <sub>2</sub>	Hardened steel ≥ 55 HRC	1.2379	X153CrMoV12	AISI D2																	