



CrazyDrill Crosspilot - 2 x d (nominal)

RECOMMENDATION FOR USE
● Excellent | ● Good | ○ Acceptable | ☒ Not recommended



DRILLING WITH EXTERNAL COOLING | CUTTING DATA OVERVIEW



Materials group	Material	Mat. no.	DIN	AISI/ASTM/UNS	V _c [m/min] [SFM]	f [mm/rev] [IPR]										
						1/64" 0.4 mm .016" f	1/32" 0.8 mm .032" f	1.0 mm .039" f	1/16" 1.5 mm .059" f	Ød1 2.0 mm .079" f	1/8" 3.0 mm .118" f	5/32" 4.0 mm .158" f	3/16" - 7/32" 5.0 mm .197" f	1/4" 6.0 mm .236" f		
P	Unalloyed carbon steel Rm < 800 N/mm²	1.0301	C10	AISI 1010	80 262											
		1.0401	C15	AISI 1015												
		1.1191	C45E/CK45	AISI 1045												
		1.0044	S275JR	AISI 1020												
		1.0715	11SMn30	AISI 1215												
	Low alloyed steel Rm > 900 N/mm²	1.5752	15NiCr13	ASTM 3415 / AISI 3310	60 197											
		1.7131	16MnCr5	AISI 5115												
		1.3505	100Cr6	AISI 52100												
		1.7225	42CrMo4	AISI 4140												
		1.2842	90MnCrV8	AISI O2												
		1.2379	X153CrMoV12	AISI D2												
		1.2436	X210CrW12	AISI D4/D6												
High alloyed tool steel Rm < 1200 N/mm²	1.3343	HS6-5-2C	AISI M2 / UNS T11302	50 164												
	1.3355	HS18-0-1	AISI T1 / UNS T12001													
	1.4016	X6Cr17	AISI 430 / UNS S43000		40 131											
	1.4105	X6CrMoS17	AISI 430F													
	Stainless steel martensitic	1.4034	X46Cr13		AISI 420C	50 164										
		1.4112	X90CrMoV18		AISI 440B											
Stainless steel martensitic – PH	1.4542	X5CrNiCuNb 16-4	AISI 630 / ASTM 17-4 PH	30 98												
	1.4545	X5CrNiCuNb 15-5	ASTM 15-5 PH													
Stainless steel austenitic	1.4301	X5CrNi 18-10	AISI 304													
	1.4435	X2CrNiMo 18-14-3	AISI 316L													
	1.4441	X2CrNiMo 18-15-3	AISI 316LM													
	1.4539	X1NiCrMoCu 25-20-5	AISI 904L													
K	Cast iron	0.6020	GG20	ASTM 30	80 262											
		0.6030	GG30	ASTM 40B												
		0.7040	GGG40	ASTM 60-40-18												
		0.7060	GGG60	ASTM 80-60-03												
		3.2315	AlMgSi1	ASTM 6351		125 410										
3.4365	AlZnMgCu1.5	ASTM 7075														
N	Aluminium alloy wrought	3.2163	GD-AlSi9Cu3	ASTM A380	125 410											
		3.2381	GD-AlSi10Mg	UNS A03590												
	Copper	2.004	Cu-OF / CW008A	UNS C10100	80 262											
		2.0065	Cu-ETP / CW004A	UNS C11000												
	Brass lead free	2.0321	CuZn37 CW508L	UNS C27400	80 262											
		2.036	CuZn40 CW509L	UNS C28000												
	Brass, Bronze Rm < 400 N/mm²	2.0401	CuZn39Pb3 / CW614N	UNS C38500	100 328											
		2.102	CuSn6	UNS C51900												
	Bronze Rm < 600 N/mm²	2.0966	CuAl10Ni5Fe4	UNS C63000	80 262											
		2.096	CuAl9Mn2	UNS C63200												
S ₁	Super alloys	2.4856		Inconel 625												
		2.4668		Inconel 718												
		2.4617	NiMo28	Hastelloy B-2												
		2.4665	NiCr22Fe18Mo	Hastelloy X												
S ₂	Titanium pure	3.7035	Gr.2	ASTM B348 / F67	25 82											
		3.7065	Gr.4	ASTM B348 / F68												
S ₃	Titanium alloys	3.7165	TiAl6V4	ASTM B348 / F136	25 82											
		9.9367	TiAl6Nb7	ASTM F1295												
H ₁	Hardened steel < 55 HRC	2.4964	CoCr20W15Ni	Haynes 25												
			CrCoMo28	ASTM F1537												
H ₂	Hardened steel ≥ 55 HRC	1.2510	100MnCrMoW4	AISI O1	20 66											
		1.2379	X153CrMoV12	AISI D2												