




SST-Inox - 30 x d

RECOMMENDATION FOR USE
● Excellent | ● Good | ○ Acceptable | ☒ Not recommended



DRILLING WITH INTEGRATED COOLING | CUTTING DATA OVERVIEW



Materials group	Material	Mat. no.	DIN	AISI/ASTM/UNS	v _c [m/min]		Q ₁	Q ₂	f [mm/rev]													
					∅d1 ≤ 0.4	∅d1 > 0.4			0.2 mm	0.4 mm	0.6 mm	∅d1	1.0 mm	1.5 mm	2.0 mm							
									f	1/64"	f	0.8 mm	f	1/32"	f	1/16"	f					
P	Unalloyed carbon steel Rm < 800 N/mm ²	1.0301	C10	AISI 1010					Recommended: CrazyDrill Flex Steel 30 x d1													
		1.0401	C15	AISI 1015																		
		1.1191	C45E/CK45	AISI 1045																		
		1.0044	S275JR	AISI 1020																		
		1.0715	11SMn30	AISI 1215																		
	Low alloyed steel Rm > 900 N/mm ²	1.5752	15NiCr13	ASTM 3415 / AISI 3310																		
		1.7131	16MnCr5	AISI 5115																		
		1.3505	100Cr6	AISI 52100																		
		1.7225	42CrMo4	AISI 4140																		
		1.2842	90MnCrV8	AISI O2																		
	High alloyed tool steel Rm < 1200 N/mm ²	1.2379	X153CrMoV12	AISI D2																		
		1.2436	X210CrW12	AISI D4/D6																		
		1.3343	HS6-5-2C	AISI M2 / UNS T11302																		
M	Stainless steel ferritic	1.4016	X6Cr17	AISI 430 / UNS S43000	30 – 40	40 – 50	2xd1 – 3xd1	0.5xd1	0.015 – 0.020	0.015 – 0.020	0.020 – 0.030	0.020 – 0.030	0.030 – 0.040	0.040 – 0.050	0.050 – 0.060							
		1.4105	X6CrMoS17	AISI 430F																		
	Stainless steel martensitic	1.4034	X46Cr13	AISI 420C	20 – 30	30 – 40	2xd1 – 3xd1	0.5xd1	0.015 – 0.020	0.015 – 0.020	0.020 – 0.025	0.020 – 0.025	0.025 – 0.035	0.040 – 0.050	0.050 – 0.060							
		1.4112	X90CrMoV18	AISI 440B																		
	Stainless steel martensitic – PH	1.4542	X5CrNiCuNb 16-4	AISI 630 / ASTM 17-4 PH	20 – 30	30 – 40	2xd1 – 3xd1	0.5xd1	0.015 – 0.020	0.015 – 0.020	0.020 – 0.025	0.020 – 0.025	0.025 – 0.035	0.040 – 0.050	0.050 – 0.060							
		1.4545	X5CrNiCuNb 15-5	ASTM 15-5 PH																		
	Stainless steel austenitic	1.4301	X5CrNi 18-10	AISI 304																		
		1.4435	X2CrNiMo 18-14-3	AISI 316L	20 – 30	30 – 40	2xd1 – 3xd1	0.5xd1	0.010 – 0.020	0.010 – 0.020	0.015 – 0.025	0.020 – 0.030	0.025 – 0.035	0.035 – 0.045	0.045 – 0.055							
		1.4441	X2CrNiMo 18-15-3	AISI 316LM																		
	K	Cast iron	0.6020	GG20	ASTM 30					Recommended: CrazyDrill Flex Steel 30 x d1												
0.6030			GG30	ASTM 40B																		
0.7040			GGG40	ASTM 60-40-18																		
0.7060			GGG60	ASTM 80-60-03																		
N	Aluminium alloy wrought	3.2315	AlMgSi1	ASTM 6351					Recommended: CrazyDrill Flex Steel 30 x d1													
		3.4365	AlZnMgCu1.5	ASTM 7075																		
	Aluminium alloy cast	3.2163	GD-AlSi9Cu3	ASTM A380																		
		3.2381	GD-AlSi10Mg	UNS A03590																		
	Copper	2.004	Cu-OF / CW008A	UNS C10100	20 – 30	35 – 60	2xd1 – 3xd1	0.5xd1								0.040	0.045	0.050	0.060	0.070	0.080	0.100
		2.0065	Cu-ETP / CW004A	UNS C11000																		
	Brass lead free	2.0321	CuZn37 CW508L	UNS C27400	20 – 30	35 – 60	2xd1 – 3xd1	0.5xd1								0.040	0.045	0.050	0.060	0.070	0.080	0.100
		2.036	CuZn40 CW509L	UNS C28000																		
	Brass, Bronze Rm < 400 N/mm ²	2.0401	CuZn39Pb3 / CW614N	UNS C38500												Recommended: CrazyDrill Flex Steel 30 x d1						
		2.102	CuSn6	UNS C51900																		
Bronze Rm < 600 N/mm ²	2.0966	CuAl10Ni5Fe4	UNS C63000																			
	2.096	CuAl9Mn2	UNS C63200																			
S ₁	Super alloys	2.4856		Inconel 625	10 – 20	20 – 30	2xd1 – 3xd1	0.2xd1	0.010 – 0.020	0.010 – 0.020	0.015 – 0.025	0.020 – 0.030	0.025 – 0.035	0.035 – 0.045	0.045 – 0.055							
		2.4668		Inconel 718																		
		2.4617	NiMo28	Hastelloy B-2																		
		2.4665	NiCr22Fe18Mo	Hastelloy X																		
S ₂	Titanium pure	3.7035	Gr.2	ASTM B348 / F67					Recommended: CrazyDrill Flex Titanium 30 x d1													
		3.7065	Gr.4	ASTM B348 / F68																		
S ₃	Titanium alloys	3.7165	TiAl6V4	ASTM B348 / F136																		
		9.9367	TiAl6Nb7	ASTM F1295																		
H ₁	Hardened steel < 55 HRC	2.4964	CoCr20W15Ni	Haynes 25	20 – 30	30 – 40	2xd1 – 3xd1	0.5xd1	0.010 – 0.020	0.010 – 0.020	0.015 – 0.025	0.020 – 0.030	0.025 – 0.035	0.035 – 0.045	0.045 – 0.055							
			CrCoMo28	ASTM F1537																		
H ₂	Hardened steel ≥ 55 HRC	1.2510	100MnCrMoW4	AISI O1																		
		1.2379	X153CrMoV12	AISI D2																		